

cempoint

gun injected mortar (paving)

FEATURES & BENEFITS



For jointing flags and different types of paving



Workability: 45 minutes



Set time: 6 hours



BS 7533 compliant



Joint widths: 5-25mm



Just add water



Available in 10 colours



APPLICATIONS

UltraScape cempoint is a cementitious gun injected pointing mortar that conforms to the strict demands of BS 7533. Specifically formulated for the jointing of flags and various different types of paving, the product is also shrinkage compensated, economical, fast and easy to apply, thus reducing costs and minimising downtime.

TECHNICAL

UltraScape cempoint is pre-blended with specialist cements and graded fillers and supplied in 25kg paper bags. The simple addition of water produces a gun injected pointing mortar, which has excellent compatibility and is resistant to freeze-thaw weather conditions. UltraScape cempoint is suitable for joint widths of between 5-25mm and in joint depths of 25-100mm.

PREPARATION

All joints must be free from any loose debris, clean and pre-soaked with water. Remove all ponded water prior to application but ensure that joints remain wet while the product is use.

MIXING

Place up to 4 litres of clean water into a suitable drum or forced action mixer. Add the contents of the 25kg bag of UltraScape

cempoint and mix between 3-5 minutes to achieve an even smooth mix. Allow material to stand for 5 minutes before application.

PLACING

Transfer material into a wet mortar gun with a trowel. Ensure there is good contact with substrate during application. Move steadily along the prepared joints to ensure a quality finish.

FINISHING

UltraScape cempoint should be tooled off whilst wet to the required profile by the use of a standard pointing tool. Ensure all material is removed from the face whilst still wet. The area can accept pedestrian traffic after 12 hours and vehicular traffic after 24 hours.

PRECAUTIONS

Please note: a small trial should be done to ensure compatibility with the stone/paving being used as Instarmac cannot test all stone/paving types. Wash all tools frequently. Mix only enough material to apply in 4 minutes.

Never remix or add extra water. Wear protective clothing. Avoid skin and eye contact - wet cement can burn the skin. Cool temperatures retard, warm temperatures accelerate.

PRODUCT AND TECHNICAL DATA

Unit/packaging	25kg bags delivered on shrink-wrapped pallets
Storage	Store in a cool, dry and frost free area at temperatures between 5°C and 30°C
Yield	14.5 litres approx, per 25kg bag
Workability*	45 minutes
Shelf life	8 months from the date of manufacture printed on the bag unopened in the above conditions. High temperatures and high humidity will reduce shelf life.
Bond (Adhesion strength)	>1.5N/mm ² after 28 days
Water required	4 litres per 25kg
Compressive strength	49.6N/mm ² after 28 days
Flexural strength	8.3N/mm ² after 28 days
Modulus of elasticity	16800
Shrinkage	0.1%
Colour*	Natural, Light Brown, Light Grey, Dark Grey, Sandstone, Yorkstone, White, Dark Brown, Brick Red, Black. Bespoke colours available upon request subject to minimum quantities

*Depending on temperatures - test carried out at 20°C. Cool temperatures retard, warm temperatures accelerate product performance. As with all raw materials, colour variation may occur. Please note that this does not affect the consistency or characteristics of the enclosed product.

HEALTH, SAFETY AND ENVIRONMENTAL

Please ensure that appropriate PPE is used when preparing, mixing and applying products. Always wash hands before consuming food and make sure that materials are kept safely out of reach of children and animals. Please dispose of packaging and waste responsibly and in accordance with local authority requirements. A full material safety data sheet relating to this product is available from instarmac.co.uk

QUALITY ASSURANCE

All products are manufactured in a plant whose quality management system is certified / registered as being in conformity with BS EN ISO 9001, ISO 14001 and ISO 45001. Our products are guaranteed against defective materials and manufacture and will be replaced or money refunded if the goods do not comply with our promotional literature. We cannot however accept responsibility arising from the application or

use of our products because we have no direct or continuous control over where and how products are used. All products are sold subject to our conditions of sales, copies of which may be obtained upon request.

CONTACT US

Instarmac Group plc, Birch Coppice Business Park, Danny Morson Way, Dordon, Tamworth, Staffordshire, B78 1SE, United Kingdom

Tel: +44 (0) 1827 254400 • Fax: +44 (0) 1827 285386 • Email: email@instarmac.co.uk • Order: orders@instarmac.co.uk • Website: instarmac.co.uk

Vers 11.10.22 Uncontrolled if printed. For the most up-to-date version of this datasheet, please refer to this product's profile on our website which can be found at www.ultrascape.co.uk